

WOODCARE WATERBASED PREMIUM INTERIOR RANGE

PRODUCT CODE: X 45-51 Range & WUT 3000/WUB 3000 Tint bases

TECHNICAL DATA SHEET

Product Description	Premium quality water based coating													
Intended Uses	Suitable for use on a wide range of interior wooden surfaces such as interior doors, furniture, skirting, counters, etc.													
Features & Benefits	<ul style="list-style-type: none"> • Easy to apply, quick-drying and non- hazardous. • Penetrates and rejuvenates wood. • Low odour. • Resistant to household stains. • Low-build finish that maintains the natural appearance of wood. • Excellent adhesion to suitably prepared new and previously painted wood. • Available in Gloss and Suede finishes. • Clear, 5 Standard colours and Transparent T/bases available for in store tinting. 													
Product Information	<p>Appearance Colours</p> <p>Tint bases Volume Solids Recommended DFT Recommended WFT Theoretical spreading rate Practical spreading rate</p> <p>TVOC</p>	<p>Milky in wet state but dries to a clear. Clear Gloss (X 45), Clear Suede (X 51), Light Oak (X 46), Teak (X 47), Oregon Pine (X 48), Imbuia (X 49) and Mahogany (X 50). Gloss Tint base (WUT 3000), Suede Tint base (WUB 3000).</p> <p>45% 20 - 30 µm 44 - 67 µm 18 m²/L per coat @ 25 µm DFT. This serves as a guide only The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used.</p> <p>50 g/L</p>												
Application Details	<p>Mixing Method Thinning Cleaning Drying time</p> <p>Application Environment</p>	<p>Stir thoroughly with a flat paddle until homogeneous.</p> <p>Brush.</p> <p>Not recommended. Ready for use.</p> <p>Water Touch dry: 30 min @ 23 °C Over coating: 4 h @ 23 °C</p> <table border="1"> <tr> <th>Surface Temperature</th><th>Ambient Temperature</th><th>Relative Humidity</th></tr> <tr> <td>Min: 10 °C</td><td>Min: 10 °C</td><td>Min: 10%</td></tr> <tr> <td colspan="3">or 2 °C min. above dew point</td></tr> <tr> <td>Max: 40 °C</td><td>Max: 40 °C</td><td>Max: 85%</td></tr> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	or 2 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85%
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10%												
or 2 °C min. above dew point														
Max: 40 °C	Max: 40 °C	Max: 85%												
Storage & Packaging	<p>Store away from direct sun, heat and severe cold. Packaging: 1L and 5L.</p>													
Tinting Procedure	<ul style="list-style-type: none"> • Select the required colour and reference no. from the WOODCARE COLOUR CARD and locate the applicable formulation from the tables. • Select the required tint base and volume for tinting and set the tinting machine to deliver the correct amount of colourants as per formulation. • Inject all required colourants, close container and shake on mechanical shaker for 5 minutes. • Note: COLOURS MUST BE TINTED FROM THE PRESCRIBED TINT BASES – WUT 3000 AND WUB 3000. • Colours may differ from the WOODCARE COLOUR CARD depending on the type and condition of the wood, as well as, the amount of coats applied 													

WOODCARE WATERBASED PREMIUM INTERIOR RANGE

PRODUCT CODE: X 45-51 Range & WUT 3000/WUB 3000 Tint bases

Surface Preparation	<p>All surfaces must be clean, dry and sound. Remove any oil, grease, mortar droppings, etc.</p> <ol style="list-style-type: none"> NEW WOOD: Sand in the direction of the grain, to a smooth finish with 150 grit paper. Remove dust with a damp cloth. PREVIOUSLY VARNISHED WOOD IN GOOD CONDITION: Sand to an even matt finish to create a key. Remove dust with a damp cloth and allow to dry. PREVIOUSLY VARNISHED WOOD IN POOR CONDITION: Remove old varnish by sanding or by using REMOVAL ALL PURPOSE PAINT REMOVER (RRA 220). If using REMOVAL rinse thoroughly with fresh water and allow to dry. Sand to a smooth finish. Remove dust with a damp cloth and allow to dry. WOOD PREVIOUSLY COATED WITH WAX SEALER/OIL BASED WOOD PRESERVATIVE: Wood coated with wax sealer or oil based preservative should not be varnished. PREVIOUSLY PAINTED WOOD: Strip old paint by deep sanding to bare wood or by using REMOVAL ALL PURPOSE PAINT REMOVER (RRA 220). If using REMOVAL rinse thoroughly with freshwater and allow to dry. Sand bare wood to a smooth finish. Remove dust with a damp cloth and allow to dry. DISCOLOURED OR WEATHERED WOOD: Remove discoloured or weathered layer by sanding with 100 grit paper. Sand bare wood to a smooth finish with 150 grit paper. Remove dust with a damp cloth and allow to dry. KNOTS IN WOOD: Clean off Resin with LACQUER THINNERS (ILS 1). Apply Plascon WOODCARE KNOT SEAL (PK 2). Allow to dry.
Application	<ul style="list-style-type: none"> NOTE: Do not thin WOODCARE WATERBASED PREMIUM INTERIOR- ready for use. Do not apply in a dusty environment. Apply the first coat by brush. Allow to dry for 4 hours. Sand lightly between coats with fine paper to de-nib. Remove dust with damp cloth and allow to dry. Apply second coat in the same manner. Apply at least 2 coats to new and old wood.
Caution	<ul style="list-style-type: none"> Wood previously coated with wax sealer should not be varnished. NB: Freshly painted doors must be allowed to dry for at least 12 hours at 23 °C before closing.
Safety Precautions	<ul style="list-style-type: none"> Always keep paint out of reach of children. Ensure good ventilation during application and drying. If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner. Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention. Harmful if swallowed. Seek medical attention and do not induce vomiting. Refer to Safety Data Sheet for complete information.

DISCLAIMER:

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,
Factoria, Krugersdorp
South Africa
1739.

Tel: +27 11 951 4500

Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za

