

PROFESSIONAL FILLERCOAT

PRODUCT CODE: PP 500

TECHNICAL DATA SHEET

Product Description	An economical good opacity acrylic coating.														
Intended Uses	A filler coat for application to suitably primed new cement plaster walls.														
Features & Benefits	<ul style="list-style-type: none">For interior use only.Seals and partly fills surface texture and assists in producing a smoother finish when over coated.Quick drying with good opacity.														
Product Information	Appearance	Smooth matt													
	Colour	White													
	Volume solids	22%													
	S G	1,52 kg/ℓ (typical)													
	Viscosity at 23 °C	Approx. 114 - 120 KU													
	Recommended DFT	20 - 30 µm													
	Recommended WFT	91 - 136 µm													
	Theoretical spreading rate	8.8 m²/L @ 30 µm DFT													
	Practical spreading rate	Practical spreading rate will vary depending on profile of the substrate, as well as the application technique and tools used													
	VOC	0 g/L													
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous.													
	Method	Brush or roller.													
	Thinning	Not recommended.													
	Cleaning	Water.													
	Drying time	Touch dry: 30 min @t 23 °C Over coating: 1 h @ 23 °C													
	Application Environment	<table><tr><td>Surface Temperature</td><td>Ambient Temperature</td><td>Relative Humidity</td></tr><tr><td>Min: 10 °C</td><td>Min: 10 °C</td><td>Min: 10%</td></tr><tr><td colspan="3">Or 2 °C min. above dew point</td></tr><tr><td>Max: 35 °C</td><td>Max: 35 °C</td><td>Max: 85%</td></tr></table>		Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	Or 2 °C min. above dew point			Max: 35 °C	Max: 35 °C	Max: 85%
Surface Temperature	Ambient Temperature	Relative Humidity													
Min: 10 °C	Min: 10 °C	Min: 10%													
Or 2 °C min. above dew point															
Max: 35 °C	Max: 35 °C	Max: 85%													
Storage and Packaging	Store away from direct sun, heat and severe cold. Packaging: 20L														
Surface Preparation	Ensure that surfaces are dry, sound, and free from dust, dirt, grease and oil before painting 1. NEW CEMENT PLASTER: Remove any loose particles and laitance by most suitable means. NB: Soft, under bound and friable surfaces must be restored to a sound condition with PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700) or PLASCON MULTI-SURFACE PRIMER (WUP 1) 2. FILLING: Fill all imperfections with POLYCELL POLYFILLA INTERIOR or POLYCELL POLYFILLA MENDALL 90														
Application	<ul style="list-style-type: none">Apply two full coats to suitably primed surfaces so as to achieve good obliteration.														
Cautions	<ul style="list-style-type: none">Do not apply to bare metal surfaces.														

PROFESSIONAL FILLER COAT

PRODUCT CODE: PP 500

Safety Precautions

- Keep out of reach of children.
 - Ensure good ventilation during application and drying.
 - In case of skin contact, wash with soap and water or a recognised skin cleaner.
 - Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.
 - Harmful if swallowed. Do not induce vomiting. Seek medical attention.
 - Refer to Safety Data Sheet for complete information.
-

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,
Factoria, Krugersdorp
South Africa
1739.
Tel: +27 11 951 4500
Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za