

# HYSHEEN ROAD MARKING PAINT - SANS 731

PRODUCT CODE: TP 24, 41 & 88

## TECHNICAL DATA SHEET

<b>Product Description</b>	Single pack solvent-based coatings for the marking of road surfaces.													
<b>Intended Uses</b>	<ul style="list-style-type: none"> <li>Used for the marking of traffic lanes.</li> <li>Suitable for use on bituminous road surfaces.</li> <li>Adjust application rate when drop-on beads are used.</li> <li>CAUTION: Not recommended for friable slurry type surfaces.</li> </ul>													
<b>Features &amp; Benefits</b>	<ul style="list-style-type: none"> <li>Complies with specification SANS 731.</li> <li>Quick drying matt finish.</li> <li>Excellent adhesion and coverage on suitably prepared surfaces.</li> <li>Good durability and resistance to abrasion.</li> <li>Suitable for, airless or pressure-feed spraying and for brush and roller application.</li> </ul>													
<b>Product Information</b>	<p>Appearance Colours</p> <p>Generic type Volume Solids Viscosity at 23 °C S G at 23 °C Recommended DFT Recommended WFT Theoretical spreading rate Practical spreading rate</p> <p>VOC</p>	<p>Matt White (TP 24), Golden Yellow SABS B49 (TP 41) and Signal Red SABS A11 (TP 88) Modified alkyd Approx. 52.4 % (typical for White) 85-90 KU (typical) 1,43 (typical for White) 230 – 250 µm without beads. 439 – 477 µm without beads 2.2 m²/L @ 240 µm without beads The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used. Should drop on beads be required the spreading rate, WFT and DFT should be adjusted to accommodate this. 404 g/L</p>												
<b>Application Details</b>	<p>Mixing Method Thinning Cleaning Drying time</p> <p>Application Environment</p>	<p>Stir thoroughly with a flat paddle until completely homogeneous. Airless or pressure-feed spraying equipment. Brush and roller. Thinning not recommended Clean equipment with <b>TOLUOL REDUCER (HVL 1)</b> or <b>NO. 40 LACQUER THINNER (ILS 1)</b>. Dry to no pick up: 20 mins at 23 °C Over coating: 1 h at 23 °C Dry to handle: 1 h at 23 °C</p> <table border="1"> <tr> <td>Surface Temperature</td><td>Ambient Temperature</td><td>Relative Humidity</td></tr> <tr> <td>Min: 10 °C</td><td>Min: 10 °C</td><td>Min: 10 %</td></tr> <tr> <td colspan="3">or 3 °C min. above dew point</td></tr> <tr> <td>Max: 40 °C</td><td>Max: 40 °C</td><td>Max.: 80%</td></tr> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10 %	or 3 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max.: 80%
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10 %												
or 3 °C min. above dew point														
Max: 40 °C	Max: 40 °C	Max.: 80%												
<b>Storage and Packaging</b>	<p>Store away from direct sun, heat and severe cold.</p> <p>Packaging 1 L, 5 L, 20 L and 200 L.</p>													

## HYSHEEN ROAD MARKING PAINT – SANS 731

PRODUCT CODE: TP 24, 41 & 88

<b>Surface Preparation</b>	<p>Surfaces must be clean, dry and sound.</p> <p><b>1. NEW ASPHALT SURFACES</b></p> <ul style="list-style-type: none"> <li>For <b>permanent markings</b> ensure that bituminous screeds have cured for a minimum of three months.</li> <li><b>NOTE:</b> Paints applied over bituminous screeds less than three months old are to be regarded as <b>temporary markings</b>.</li> </ul> <p><b>2. PREVIOUSLY COATED ASPHALT SURFACES</b></p> <ul style="list-style-type: none"> <li>Remove loose and flaking paint.</li> <li>Remove oil, grease and other contaminants with <b>POLYCELL SUGAR SOAP LIQUID</b>. Rinse thoroughly with fresh water and allow to dry.</li> </ul>
<b>Application</b>	<ul style="list-style-type: none"> <li>Apply a 477 µm WFT to achieve complete coverage.</li> <li>Should complete coverage not be achieved with one coat, apply a second coat.</li> </ul>
<b>Caution</b>	<ul style="list-style-type: none"> <li><b>NOT</b> recommended for friable slurry-type surfaces.</li> <li>Can only be applied on cured bitumen, bleeding may occur on fresh bitumen.</li> <li><b>NB: Not recommended for concrete surfaces</b> but if required then use the following preparation first: <ul style="list-style-type: none"> <li>1. Remove laitance mechanically by high speed diamond grinding to create a key. Dust off well.</li> <li>2. Seal with <b>GEHOPON SEALER (GW 7)</b> or <b>CONCRETE FLOOR PREP (FCS 1)</b>.</li> <li>3. The recommended product for concrete and concrete pavers is <b>BRICK &amp; CONCRETE MARKING PAINT (BTP 1)</b>.</li> </ul> </li> <li>Always keep containers tightly closed when not in use, since solvents evaporate very fast.</li> </ul>
<b>Safety Precautions</b>	<ul style="list-style-type: none"> <li>Always keep paint out of reach of children.</li> <li>Ensure good ventilation during application and drying.</li> <li>If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner.</li> <li>Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention.</li> <li>Harmful if swallowed. Seek medical attention and do not induce vomiting.</li> <li>Do not smoke while painting.</li> <li>Flammable. Store in a cool dry place away from heat and sparks.</li> <li>Refer to Safety Data Sheet for complete information.</li> </ul>

### DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

**NB:** Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

**NB: TO ORDER:** Quote product name, product code number, packaging and colour.

### KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,  
Fatoria, Krugersdorp  
South Africa  
1739.

Tel: +27 11 951 4500

Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za