

CATALYST FOR PLASCOTHANE 9-1

PRODUCT CODE: KAT 518

TECHNICAL DATA SHEET

Product Description	Aliphatic polyisocyanate catalyst for 2 pack polyurethane systems	
Intended Uses	Used to catalyse the PLASCOTHANE 9-1 INDUSTRIAL POLYURETHANE ENAMEL (UP Series)	
Product Information	Colour:	Water white/Clear
	Specific Gravity:	1.04
	Pot Life:	6 hours @ 23 °C
Application Details	Mixing	Mixing Ratio: 9 parts UP Series to 1 part KAT 518 by volume
Storage and Packaging:	Should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30 °C. Exposure to direct sunlight should be avoided.	
Cautions	<ul style="list-style-type: none"> • This material is flammable. • Do not inhale vapours. 	
Safety Precautions	<ul style="list-style-type: none"> • Keep out of reach of children. • Ensure good ventilation during application and drying. • In case of skin contact, wash with soap and water or a recognised skin cleaner. • Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist. • Harmful if swallowed. Do not induce vomiting. Seek medical attention. • Do not smoke while painting. • Flammable. Store in a cool dry place away from heat and sparks. • Refer to Safety Data Sheet for complete information 	

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,
Factoria, Krugersdorp.
1739.

Tel: 011 951 4500

Fax: 0800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za