

# PLASCOLAC MDF EDGE SEALER

**PRODUCT CODE: EZN 1009** 

## **TECHNICAL DATA SHEET**

Dunduct Decement:	A COLOR OF THE COLOR		
Product Description	Acid catalysed edge sealer		
Intended Uses	This lacquer is formulated as edge sealers for use on all interior MDF wood substrates.		
Features & Benefits	Fast drying Lacquers		
	<ul> <li>Excellent sealing of interest</li> </ul>	erior timber substrates	
	<ul> <li>Good sanding character</li> </ul>	ristics.	
Product Information	Viscosity at 23°C	22-24" (Catalysed) "Ford Cup No 4	
	Specific Gravity at 23°C	0.90 - 0.95	
	Flash Point	< 23 °C	
	Pot Life	12 hours	
	Theoretical spreading rate	100 - 120 g/m² per coat.	
Application Details	Mixing:	Catalyst KAT 1104. Mixing Ratio: 24:1 by Volume	
	Method:	Conventional spray and air assisted airless.	
		The recommended air pressures are as follows: -	
		Air Assisted Airless:	
		Pump pressure 1.5 - 2 bar. Atomising air pressure 1 - 1.5 bar	
		Conventional Spray:	
		Pressure pot pressure 1 - 1.5 bar. Atomising air pressure 1.5 bar	
	Thinning	Use UNIVERSAL REDUCER (PUR 1)	
	Cleaning	Clean all equipment immediately after use with No 40 LACQUER THINNERS	
		(ILS 1)	
	Drying time:	Air dry at 23 °C & 65 % Relative Humidity	
		Dust free: 8 -12 min @ 23 °C	
		Handle: 35 - 40 min @ 23 °C	
		Sand:40 -45 min	
		Stack/ Rack: Overnight	
		Wrap: 24 h	
		Accelerated drying time & temp	
		Flash off: 5 - 8 min, 25 – 30 °C	
		Oven: 40 - 60 min, 35 – 55 °C	
		Cool: 15 min, 25 – 28 °C	
		Sand: Once cooled, 25 °C	
		Stack/Rack: Once cooled, 25 °C	
Storage and Packaging	Store away from direct sun, heat and severe cold.		
	Packaging: 4.8 L 24 L and 192	2L	
Surface Preparation	Surface must be dry, clean and free of contaminants.		
	Sand to a smooth surface, free of loose fibres.		
	Remove all dust prior to the application of the basecoat.		
	Recommended Topcoats: EZN 1000 SERIES & other EZN TOPCOATS		



TDS: EZN 1009 Version: 4.00 Revision date: 18/03/2018 Page 1 of 2



## PLASCOLAC MDF EDGE SEALER

**PRODUCT CODE: EZN 1009** 

Application	Apply at a rate of 100 - 120 g/m² per coat.
	Allow the coating to dry as specified.
	Sand with 280 or 320 grit finishing paper.
	Remove all sanding dust prior to further application.
Cautions	This material is flammable and must not be exposed to naked flame.
Safety Precautions	Keep out of reach of children.
	<ul> <li>Ensure good ventilation during application and drying.</li> </ul>
	<ul> <li>In case of skin contact, wash with soap and water or a recognised skin cleaner.</li> </ul>
	Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical
	advice if symptoms persist.
	Harmful if swallowed. Do not induce vomiting. Seek medical attention.
	Refer to Safety Data Sheet for complete information.

#### DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

**NB:** Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

### KANSAI PLASCON (PTY) LTD

10 Frederick Cooper Drive, Factoria, Krugersdorp South Africa 1739.

Tel: +27 11 951 4500 Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za



TDS: EZN 1009 Version: 4.00 Revision date: 18/03/2018 Page 2 of 2