

BLACK TOP CATALYST FOR PLASCOLAC REACTION LACQUER

PRODUCT CODE: KAT 1371

TECHNICAL DATA SHEET

Product Description	A blended Sulphonic acid catalyst	
Intended Uses	Used to catalyse the PLASCOLAC range of products. It is recommended for temperatures between 0 °C – 16 °C.	
Product Information	Colour:	Light straw
	Specific Gravity:	0.925
	Pot Life:	12 hours
	Flash Point:	< 12 °C
Application Details	Mixing	Mixing Ratio: 24 parts PLASCOLAC to 1-part KAT 1371 by volume
Storage and Packaging:	Store away from direct sun, heat and severe cold 1 L.	
Cautions	<ul style="list-style-type: none"> • Caution. If used in temperatures above 16 °C product will dry rapidly resulting in compromise in ideal flow, levelling and Gloss. • This material is flammable and contains acid and must not be exposed to naked flame. • Do not inhale vapours. 	
Safety Precautions	<ul style="list-style-type: none"> • Keep out of reach of children. • Ensure good ventilation during application and drying. • In case of skin contact, wash with soap and water or a recognised skin cleaner. • Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist. • Harmful if swallowed. Do not induce vomiting. Seek medical attention. • Do not smoke while painting. • Flammable. Store in a cool dry place away from heat and sparks. • Refer to Safety Data Sheet for complete information 	

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LTD

10 Frederick Cooper Drive,
Factoria, Krugersdorp
South Africa
1739.
Tel: +27 11 951 4500
Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za