

WOODFINISH POLYURETHANE CLEAR SEALER

PRODUCT CODE: UPF 1000

TECHNICAL DATA SHEET

Product Description	UPF 1000 is dual pack polyurethane acrylic finish.				
Intended Uses	Recommended for use on interior and exterior wooden furniture, office furniture and timber				
Features & Benefits	Quick drying - touch dry in 30 minutes.				
	Non-yellowing				
Product Information	Appearance	Matt			
	Colour	Clear (UPF 1000)			
	Generic type	Acrylic			
	Solvents type	Aromatic hydrocarbons, acetates and esters			
	Solids (Catalysed)	Approx. 49 % by volume			
	S G at 23 °C	Approx. 0.99 kg/L			
	Recommended DFT	25 - 40 μm per coat			
	Recommended WFT	51 – 82 μm per coat			
	Spread rate	100 - 120 g/m ² per coat			
	Viscosity at 23 °C (Catalysed)	70 – 80 secs			
	Flash Point	23 °C			
	Pot-life	4 h			
	VOC	553 g/L			
Application Details	Mixing	Stir base with a flat paddle until homogeneous. Mix in ratio supplied, viz			
		4 parts BASE to 1 part CATALYST (KAT 400) by volume.			
	Method	Conventional spray, air assisted airless or a pressure pot system.			
		The recommended air pressures are as follows: -			
		Air Assisted Airless: Pump pressure 1.5 - 2 bar			
		Atomising air pressure 1 - 1.5 bar			
		Pressure Pot: Pressure pot pressure 1 - 1.5 bar			
		Atomising air pressure 1.5 bar			
		Use only stainless-steel spray application equipment. Nozzle sizes: 1.4		1.4 -	
		1.8 mm.			
	Thinning	For conventional spraying thin with UNIVERSAL REDUCER (PUR 1) to a			
	5	spraying viscosity of approximately 18 seconds at 23 °C in a Ford Cup I			
		4. Use approximately 20 % thinner to obtain the correct viscosity.			•
	Cleaning	No 40 LACQUER THINNERS (ILS 1) or UNIVERSAL REDUCER (PUR 1)			
	Drying Times	Touch dry: 30 min @ 23 °C			
	, 5	Dry to handle: 4 h @ 23 °C			
		Full cure: 7 days			
		· · · · · · · · · · · · · · · · · · ·			
	Application Environment	Surface	Surface	Relative	
		Temperature	Temperature	Humidity	
		Min: 10 °C	Min: 10 °C	Min: 10 %	
		Or 3 °C above due point			
		Max: 40 °C	Max: 40 °C	Min: 85 %	
			IVIAA. 40 C	IVIIII. 0J /0	
<u></u>	Change and for a direction of the				
Storage and Packaging	Store away from direct sun, heat	and severe cold.			





WOODFINISH POLYURETHANE CLEAR SEALER

PRODUCT CODE: UPF 1000

Surface Preparation	Surface must be dry, clean and free of contaminants.		
-	• Sand to a smooth surface, free of loose fibres.		
	• Sand substrate with 150 – 180 grit paper to a smooth finish		
	Remove all dust prior to application.		
Application	• If application equipment was used previously for solvent based products, ensure all equipment is washed		
	thoroughly, first with lacquer thinners and then water before use.		
	 Apply at a rate of 100 - 120 g/m² per coat. Do not apply more than 180 g/m2 		
	Allow the coating to dry as specified.		
	Sand with 280 or 320 grit finishing paper.		
	Remove all sanding dust prior to further application		
Cautions	• Do not apply PLASCOTHANE WOODFINISH POLYURETHANES directly to acrylic lacquers and synthetic		
	alkyd enamels.		
Safety Precautions	Always keep paint out of reach of children.		
	Ensure good ventilation during application and drying.		
	• If accidental contact with skin should occur, wash immediately with soap and water or a recognized skin		
	cleaner.		
	• Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of		
	water and seek medical attention.		
	Harmful if swallowed. Seek medical attention and do not induce vomiting.		
	Do not smoke while painting.		
	• Flammable. Store in a cool dry place away from heat and sparks.		
	CATALYST contains isocyanate – use suitable respirator, particularly during spray application of the mixed		
	material.		
	Refer to Safety Data Sheet for complete information.		

DISCLAIMER:

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive, Factoria, Krugersdorp South Africa 1739. Tel: +27 11 951 4500 Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60 EMAIL: advice@kansaiplascon.co.za

