

PLASCOTHANE WOODFINISH POLYURETHANE CLEAR

PRODUCT CODE: UPF 2007

TECHNICAL DATA SHEET

Product Description	UPF 2007 is a dual pack polyurethane acrylic finish.		
Intended Uses	For interior and exterior furniture, office furniture and kitchen and bar counter tops		
Features & Benefits	An attractive smooth gloss finish that is easy to keep clean		
	Good durability		
	Good chemical resistance with good colour retention		
	Quick drying - touch dry in 30 min		
	Non-yellowing		
	Good mar resistance		
Product Information	Appearance	Full gloss	
	Colour	Clear (UPF 2007)	
	Generic type	Acrylic	
	Solvents type	Aromatic hydrocarbons, acetates and esters	
	Solids	Approx. 37 % by volume	
	S G at 23ºC	Approx. 0.98 kg/L	
	Recommended DFT	25 - 40 μm per coat	
	Recommended WFT	68 – 108 μm	
	Spread rate	100 – 120g/m ² per coat	
	Viscosity at 23 °C	115 – 120 sec	
	Flash Point	23 °C	
	Pot-life	6 h	
	VOC	531 g/L	
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous. Mix in ratio supp	
		4 parts BASE to 1 Part CATALYST (KAT 400) by volume	
	Method	Conventional spray, air assisted airless or a pressure pot system.	
		The recommended air pressures are as follows: - Air Assisted Airless: Pump pressure 1.5 - 2 bar	
		Atomising air pressure 1 - 1.5 bar	
		Pressure Pot: Pressure pot pressure 1 - 1.5 bar	
		Atomising air pressure 1.5 bar	
		Use only stainless-steel spray application equipment. Nozzle sizes 1.8mm.	
	Thinning	Use PUR 1 (PLASCON UNIVERSAL REDUCER) for thinning to a spraying	
		viscosity of approx. 18 seconds at 23 °C in Ford Cup No. 4.	
	Cleaning	PLASCON UNIVERSAL REDUCER (PUR 1) or LACQUER THINNER (ILS 1)	
	Drying time	Touch dry: 30 min. @ 23 °C (50% Relative Humidity)	
		Dry to handle: 4 h @ 23 °C Full cure: 7 days @ 23 °C	
		Full cure. 7 days @ 25°C	
		Surface Ambient Relative	
	Application Environment	Temperature Temperature Humidity	
		Or 3 °C min above dew point	
		Max: 40 °C Max: 40 °C Max: 85 %	







PLASCOTHANE WOODFINISH POLYURETHANE CLEAR

PRODUCT CODE: UPF 2007

Surface	Surface must be dry, clean and free of contaminants	
Preparation	Sand to a smooth surface, free of loose fibres	
	• Sand substrate with 150 – 180 grit sand paper to a smooth finish	
	Remove all dust prior to the application of the clear coating.	
Application	• If application equipment was used previously for water-based product, ensure all the equipment is	
	washed with water then alcohol followed by solvent LACQUER THINNERS (ILS 1).	
	 Apply at a rate of 100 – 120g/m² per coat. Do not apply more than 180g/m². 	
	Allow the coating to dry as specified.	
	• Sand with 320 – 400 grit sand paper.	
	Remove all sanding dust prior to further application.	
Caution	Do not apply directly to acrylic lacquers and synthetic alkyd enamels	
Safety Precautions	• Keep out of reach of children.	
	Ensure good ventilation during application and drying.	
	• Do not pour paint down the drain.	
	 In case of skin contact, wash with soap and water or a recognised skin cleaner. 	
	• Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical	
	advice if symptoms persist.	
	• Do not smoke while painting.	
	Harmful if swallowed. Do not induce vomiting. Seek medical attention.	
	Refer to Safety Data Sheet for complete information.	

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive, Factoria, Krugersdorp South Africa 1739. Tel: +27 11 951 4500 Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60 EMAIL: advice@kansaiplascon.co.za

