

## DESIGNER RANGE SUEDE PAINT

PRODUCT CODE: SDE Range & TSD 1000 Tint Base

### TECHNICAL DATA SHEET

<b>Product Description</b>	A waterbased premium textured interior wall paint designed to look like brushed suede.													
<b>Intended Uses</b>	<ul style="list-style-type: none"> <li>For interior use.</li> <li>For application to suitably primed smooth cement plaster walls, concrete, fibre-board, fibre cement, ceiling board and gypsum plaster.</li> <li>Ideal for feature walls in living rooms, bedrooms, studies and for use below a dado rail.</li> </ul>													
<b>Features &amp; Benefits</b>	<ul style="list-style-type: none"> <li>Faux suede finish</li> <li>Absorbs and reflects light, enhancing the textured faux suede finish.</li> <li>Fashionable colour range.</li> <li>Waterbased</li> <li>Quick Drying</li> <li>Quick drying - 2 coats can be applied in one day.</li> </ul>													
<b>Product Information</b>	Appearance Colours Tint Base Generic type Solids Recommended DFT Viscosity at 23 °C Theoretical spreading rate Practical spreading rate  VOC	Brushed suede finish Standard colours Can be tinted Using TSD 1000 Tint base Acrylic emulsion Approx. 38 % by volume Varies with the effect to be created Approx. 100 KU (typical) 8 – 10 m <sup>2</sup> /L This serves as a guide only. The practical spreading rate will vary depending on the profile of the substrate, as well as the application technique and tools used. 26 g/L												
<b>Application Details</b>	Mixing  Method Thinning Cleaning Drying time    Application Environment	Stir thoroughly with a flat paddle in a circular lifting motion for 5 minutes. Continue stirring at regular intervals during application. Brush and roller. Ready for use. Thinning not Recommended. Water Touch dry: 30 min @ 23 °C Over coating: 4 h @ 23 °C  <table border="1"> <thead> <tr> <th>Surface Temperature</th><th>Ambient Temperature</th><th>Relative Humidity</th></tr> </thead> <tbody> <tr> <td>Min: 10 °C</td><td>Min: 10 °C</td><td>Min: 10%</td></tr> <tr> <td colspan="3">Or 2 °C min. above dew point</td></tr> <tr> <td>Max: 35 °C</td><td>Max: 35 °C</td><td>Max: 85 %</td></tr> </tbody> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	Or 2 °C min. above dew point			Max: 35 °C	Max: 35 °C	Max: 85 %
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10%												
Or 2 °C min. above dew point														
Max: 35 °C	Max: 35 °C	Max: 85 %												
<b>Storage &amp; Packaging</b>	Store away from direct sun, heat and severe cold. Packaging: 1 L and 5 L													

## DESIGNER RANGE SUEDE PAINT

PRODUCT CODE: SDE Range & TSD 1000 Tint Base

Surface Preparation

1.

NEW WORK

1.1

Cement plaster, concrete, fibre-cement, ceiling boards, gypsum plaster (e.g. Rhinolite, Cretestone): Remove any loose particles and laitance by most suitable means. Prime with **PLASCON PLASTER PRIMER (UC 56)**.  
**N.B.** Soft, under bound, friable and highly porous surfaces must be restored to a sound condition using **BONDING LIQUID (CVI 14)** or **PLASCON PLASTER PRIMER (UC 56)** or by re-plastering.  
**N.B.** If a gypsum plaster has been used as the joint skimming filler on gypsum board or dry wall partitioning, then these areas must be sealed with **PLASCON PLASTER PRIMER (UC 56)**.

2.

PREVIOUSLY PAINTED SURFACES

2.1

Previously painted surfaces in good condition:

Remove loose and flaking paint back to a sound substrate and a firm edge by scraping and sanding. Spot prime bare areas with appropriate primer. Clean with **SUGAR SOAP POWDER CLEANER** solution to remove all contaminants. Rinse with clean water to remove all traces of **SUGAR SOAP**. Sand glossy enamel surfaces to a matt finish and apply one coat of **PLASCON UNIVERSAL UNDERCOAT (UC 1)**.

2.2

Previously painted surfaces in poor condition:

Completely remove paint by suitable means and treat as for new work.

3.

FILLING

Fill all imperfections with **MENDALL 90 ALL PURPOSE ADHESIVE FILLER** or **POLYFILLA INTERIOR CRACK FILLER** and spot prime filled areas with **PLASCON PLASTER PRIMER (UC 56)**.

Application

•

Apply the first coat with a long nap roller, brushing all areas that cannot be reached by roller first. To ensure a good film of paint avoid overspreading.

•

Allow at least 4 hours drying time before over coating.

•

To achieve faux suede effect, apply second coat with a good quality Hamilton’s Perfection or Professional brush (100mm), in random criss-cross strokes. Work in areas 1 – 2 square metres. Make sure to overlap criss-cross areas to ensure an even effect. Allow 30 minutes for the effect to appear.

Suede Colour	Suede Code	Polvin base coat	Colour Code
Buckskin	SDE 1	Hazelnut	O7-D2-1
Burnt Clay	SDE 2	Strand of Gold	O5-C1-4
Amber	SDE 3	Japura	O7-B1-4
African Jade	SDE 4	Kiwi	G1-C2-1
Spitfire	SDE 5	Cream of Wheat	O7-E2-1
Botanical	SDE 9	Aqua Dream	G6-D2-2
Cherry Ice	SDE 10	Fragile Petal	R5-B1-4
Coral blue	SDE 11	Overlook	B5-C2-1

Cautions

•

Suede should be applied on smooth surfaces only

•

Avoid painting during inclement weather or if temperature is below 10 °C.

•

To ensure that colours on a project are consistent check that batch numbers and product codes are the same.

## DESIGNER RANGE SUEDE PAINT

PRODUCT CODE: SDE & TSD 1000 Tint Base

---

<b>Safety Precautions</b>	<ul style="list-style-type: none"><li>• Always keep paint out of reach of children.</li><li>• Ensure good ventilation during application and drying.</li><li>• If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner.</li><li>• Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention.</li><li>• Harmful if swallowed. Seek medical attention and do not induce vomiting.</li><li>• Refer to Safety Data Sheet for complete information.</li></ul>
---------------------------	---

---

**DISCLAIMER:**

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

**N.B.** Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

**N.B. TO ORDER:** Quote product name, product code number, packaging and colour.

**KANSAI PLASCON (PTY) LTD**

10 Frederick Cooper Drive,  
Factoria, Krugersdorp  
South Africa  
1739.

Tel: +27 11 951 4500

Fax: +27 800 110 932

**PLASCON ADVISORY SERVICE:** 0860 20 40 60

**EMAIL:** [advice@kansaiplascon.co.za](mailto:advice@kansaiplascon.co.za)