

## TRADEPRO TEXTURED

PRODUCT CODE: UTX RANGE

TECHNICAL DATA SHEET

<b>Product Description</b>	A coarse, textured weather resistant paint.													
<b>Intended Uses</b>	<ul style="list-style-type: none"> <li>Weatherproofing and decorating exterior wall surfaces.</li> <li>Also used to disguise minor surface irregularities in the substrate.</li> <li>For application to well cleaned, prepared and primed concrete, cement plaster and other masonry surfaces.</li> </ul>													
<b>Features &amp; Benefits</b>	<ul style="list-style-type: none"> <li>Granular, sand textured finish</li> <li>Protects exterior surfaces against the weather and the elements</li> <li>Durable and long lasting</li> <li>Fills hairline cracks and disguises minor surface defects and repaired areas</li> <li>Its tough formulation gives a long-lasting matt finish that covers hairline cracks while maintaining its colour longer.</li> </ul>													
<b>Product Information</b>	<p>Appearance Colours</p> <p>Solids Viscosity at 23 °C Recommended DFT Recommended WFT Theoretical spreading rate Practical spreading rate</p> <p>VOC</p>	<p>Textured finish. White (UTX 1); Cream (UTX 2); Beige (UTX 3); Peach (UTX 4); Tan (UTX 5); Sand (UTX 6); Fern (UTX 7); Grey (UTX 8).</p> <p>35 % by volume Approx. 110 KU 40 – 50 µm per coat 114 – 143 µm per coat 7.8 m<sup>2</sup>/L per coat @ 45 µm DFT. This serves as a guide only The practical spreading rate will vary depending on the profile of the substrate, as well as the application technique and tools used.</p> <p>0 g/ L</p>												
<b>Application Details</b>	<p>Mixing Method</p> <p>Thinning Cleaning Drying time</p> <p>Application Environment</p>	<p>Stir thoroughly with a flat paddle until homogeneous.</p> <p>Brush or normal roller. Spray not normally recommended since the product is abrasive.</p> <p>Not recommended</p> <p>Water</p> <p>Touch dry: 1 h @ 23 °C Over coating: 2 h @ 23 °C</p> <table border="1"> <thead> <tr> <th>Surface Temperature</th><th>Ambient Temperature</th><th>Relative Humidity</th></tr> </thead> <tbody> <tr> <td>Min: 10 °C</td><td>Min: 10 °C</td><td>Min: 10 %</td></tr> <tr> <td colspan="3">Or 3 °C min. above dew point</td></tr> <tr> <td>Max: 40 °C</td><td>Max: 40 °C</td><td>Max: 85 %</td></tr> </tbody> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10 %	Or 3 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85 %
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10 %												
Or 3 °C min. above dew point														
Max: 40 °C	Max: 40 °C	Max: 85 %												
<b>Storage &amp; Packaging</b>	<p>Store away from direct sun, heat and severe cold.</p> <p>Packaging: 5 L &amp; 20 L</p>													

## TRADEPRO TEXTURED

PRODUCT CODE: UTX RANGE

TECHNICAL DATA SHEET

<b>Surface Preparation</b>	<p>Ensure that surfaces are dry, sound, and free from dust, dirt, grease and oil before painting.</p> <ol style="list-style-type: none"> <li><b>NEW WORK</b> <ol style="list-style-type: none"> <li><b>Cement plaster, concrete porous brickwork, stone work:</b> Remove any loose particles and laitance by most suitable means. Prime with <b>TRADEPRO SOLVENT BASED PLASTER PRIMER (USP 1)</b>.</li> <li><b>Fibre cement board:</b> Prime with <b>BONDING LIQUID (CV1 14)</b></li> </ol> </li> <li><b>PREVIOUSLY PAINTED SURFACES</b> <ol style="list-style-type: none"> <li><b>Previously painted surfaces in good condition:</b> Remove loose and flaking paint back to a sound substrate and a firm edge by scraping and sanding. Clean with <b>POLYCELL SUGAR SOAP POWDER</b> solution to remove all contaminants and chalked material. Rinse with clean water to remove all traces of sugar soap. Alternatively, clean with high pressure water jet. Spot prime bare areas with appropriate primer. Sand glossy enamel surfaces to a matt finish and apply one coat of <b>TRADEPRO UNDERCOAT (UWU 1)</b>.</li> <li><b>Previously painted surfaces in poor condition:</b> Completely remove paint by most appropriate means e.g. scraping, coarse sanding or stripping. Wash thoroughly with <b>POLYCELL SUGAR SOAP POWDER</b> solution. Rinse well with fresh water to remove all traces of the cleaning agents and debris. Ensure substrate is sound, not powdery or friable, prior to coating. Proceed as for <b>NEW WORK</b>.</li> </ol> </li> <li><b>FILLING</b> Fill all imperfections with the suitable <b>POLYCELL FILLER</b> and spot prime filled areas with <b>TRADEPRO SOLVENT BASED PLASTER PRIMER (USP 1)</b></li> </ol>
<b>Application</b>	<ul style="list-style-type: none"> <li>Apply two coats using a medium pile roller to primed surfaces to achieve complete obliteration and the desired textured effect.</li> <li>Always maintain a wet edge and avoid downing tools during the application process to prevent lap marks and variances in colour or texture. Work from corner to corner or from a natural cut off point to another. Do not attempt touch ups but redo complete panels.</li> </ul>
<b>Cautions</b>	<ul style="list-style-type: none"> <li>Avoid painting during inclement weather or if temperature is below 10 °C.</li> <li>For optimum performance avoid over-spreading</li> </ul>
<b>Safety Precautions</b>	<ul style="list-style-type: none"> <li>Keep out of reach of children.</li> <li>Ensure good ventilation during application and drying.</li> <li>In case of skin contact, wash with soap and water or a recognised skin cleaner.</li> <li>Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.</li> <li>Harmful if swallowed. Do not induce vomiting. Seek medical attention.</li> <li>Refer to Safety Data Sheet for complete information.</li> </ul>

### DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specified or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

**NB:** Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

**NB: TO ORDER:** Quote product name, product code number, packaging and colour.

### KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,  
 Fatoria, Krugersdorp  
 South Africa  
 1739.  
 Tel: +27 11 951 4500  
 Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za