

NEW WORK/REPAINT: REPAINT - INTERIOR
Urban and Industrial Atmospheres
Good Chemical Resistance. Production areas with high humidity – flooring – high traffic areas

SUBSTRATE: Concrete

PAINT FINISH: Plascon Plascotuff 4000 HB Floor Coating PRODUCT CODE: **FHB 4000**
(High gloss, high build solvent-free epoxy floor coating offering good chemical resistance & durability)

500µm Coating System

COLOUR: Standard colours as per colour card.

ENVIRONMENT: **The Maintenance Cycle is a guide but can vary due to micro-climate changes identified on the site which will affect the longevity of the coating system**

As per ISO 12944: Maintenance Cycle (Years)

C3

4

Plascon Coating System	Application Method	Spreading Rate m ² /ℓ	WFT/DFT µm (min & max)	Reducer/Cleaner	Overcoating time h @ 23 °C	Technical Data Sheet No	TVOC g/ℓ
Spot Sealer Coat Plascon Plascoguard Gehopon 7 Sealer (GW 7) Mixing Ratio: 5:1 by mass	B, R or S	@ 18 µm Theo – 11.7 Prac – 5.7	DFT: 15–20 WFT: 71-95	GP Epoxy Reducer (EPT 1)	12	GW 7	
Scraper Coat Plascon Plascotuff 4000 HB Floor Coating (FHB 4000) Mixing Ratio: 3:1 by volume	Trowel,	Apply @ 4 m ² /ℓ and Draw off to zero (Spread rate depends on profile)	DFT: 100 WFT: 100	GP Epoxy Reducer (EPT 1)	8-18	FHB 4000	
2nd Coat: Plascon Plascotuff 4000 HB Floor Coating (FHB 4000) Mixing Ratio: 3:1 by volume	Trowel , Notched Rake and Spiked Roller Or Mohair roller	@ 400 µm Prac – 2.5	DFT: 400 WFT: 400	GP Epoxy Reducer (EPT 1)	8-18	FHB 4000	

SURFACE PREPARATION:

- ^ After a full site assessment has been conducted, select the appropriate surface preparation required from Surface Preparation clauses for remedial procedure.

APPLICATION: SEALER AND FINAL COATS

Sealer coat:

Mix base and hardener thoroughly together in a 5:1 ratio before use.

- ^ Spot prime bare and repaired areas with Plascon Gehopon Impregnation Sealer (GW 7) by Mohair roller at a rate of not more than 7 m²/ℓ. Allow twelve (12) hours to dry. Any gloss patches should be sanded to a matt finish.

Finishing coats:

Mix base and hardener thoroughly together in a 3:1 ratio before use.

- ^ Apply two coats of Plascon Plascotuff FHB 4000 Series, first coat by trowel at a spread rate of 4 m²/ℓ, drawn down to zero, allowing overnight drying between coats.
- ^ Apply the second coat at a spread rate of 2.5 m²/ℓ (400 µm) as specified with a notched rake to achieve a total dry film thickness of approximately 500 µm or by mohair roller. Finish off by using a spiked roller whilst still wet to ensure a uniform finish is obtained and that the coating is de-aerated.
- ^ The full cure will require 7 days before heavy traffic permitted.

Note: Do not leave for longer than 24 hrs between coats.

Epoxy Coatings require 7 days to reach full chemical cure prior to being subjected to any chemical spillage. Please ensure that the complete order quantity is ordered in one batch to ensure batch colour consistency is maintained.

All coating activities must be carried out in accordance with our product data sheets.

If there is no damp course, rising damp and or moisture ingress can cause a system failure.

TABLE REFERENCES:

- ^ Technical Data Sheet (TDS): User must always ensure that latest issue is used.
- ^ B = Brush (ready for use), R = Roller (synthetic, min. 10mm pile) (ready for use), S = Airless spray (ready for use).
- ^ Theoretical spreading rate quoted is for smooth non-porous substrates and does not include allowance for surface profile, porosity, wastage and uneven film application. Suitable allowance should be made according to type of work, method and skill of applicator. Practical spreading rate quoted is an average guide only - actual must be determined by user.
- ^ Overcoating times are at 23 °C and 75 % relative humidity. Longer times must be allowed under cooler and moist conditions. DO NOT paint during inclement weather and when temperature is below 10 °C.
- ^ Fading and chalking will occur to a greater or lesser degree depending on pigmentation and generic binder type.
- ^ NB: Life expectancy may vary, depending on environmental conditions and stresses, within the macro/micro climate of the project.

Copyright ©Kansai Plascon (Pty) Ltd 2013. All rights reserved. No part of this work may in any form or by any means be reproduced without prior written permission of the copyright owner. PLASCON is the registered trade mark of Kansai Plascon (Pty) Ltd,

