

SPECIFICATION NO: **RD301t**

NEW WORK/REPAINT: REPAINT – INTERIOR / EXTERIOR

SUBSTRATE: Metals - Galvanized Iron (within 5km of the coast)

PAINT FINISH: Plascon Waterbased Velvagio (Smooth finish – water based, superior medium satin finish waterbased enamel) **PRODUCT CODE: VLW**

COLOUR: White plus Plascon colour system and other fan decks.

ENVIRONMENT: **The Maintenance Cycle is a guide but can vary due to micro-climate changes identified on the site which will affect the longevity of the coating system**

As per ISO 12944-2:1998 Maintenance Cycle (Years)

| | | |
|------|------------------|---|
| C1 - | Inland | 7 |
| C3 - | Industrial | 7 |
| C5 - | Coastal / Marine | 7 |

| Plascon Coating System | Application Method | Spreading Rate m ² /ℓ | WFT/DFT μm (min & max) | Reducer/Cleaner | Overcoating time h @ 23 °C | Technical Data Sheet No | TVOC g/ℓ |
|--|-----------------------|-----------------------------------|----------------------------|-----------------|---|-------------------------|--|
| Spot Primer Plascon Plascontuff 3000 series (PEX 3004 Grey/ PEH 3 Hardener) Mixing Ratio: 4:1 by volume | Airless Spray, R or B | 5.3 m ² /ℓ @ 153 μm | DFT 100-200 WFT 125-250 | EPT 2 | 16 min 2 weeks max See Notes below | PEX 3000 | |
| 1st Finishing Coat Plascon Waterbased Velvagio (VLW/TVW) | B, R or S | @ 35 μm Theo: 9.7 Prac: 5.5 | WFT 88-118 DFT 30-40 | Water | 4 | VLW | 46-50 white, pastel tinted < 53-60 deep & transparent tinted |
| 2nd Finishing Coat Plascon Waterbased Velvagio (VLW/TVW) | B, R or S | @ 35 μm Theo: 9.7 Prac: 5.5 | WFT 88-118 DFT 30-40 | Water | 4 | VLW | 46-50 white, pastel tinted < 53-60 deep & transparent tinted |

SURFACE PREPARATION:

- ^ After a full site assessment has been conducted, select the appropriate surface preparation required from Surface Preparation clauses for remedial procedure.
-

APPLICATION:

Primer Coat

- ^ Spot prime bare and repaired areas with Plascon Plascotuff 3000 Series (PEX 3004 Grey/PEH 3) Premix both components of the Plascon Plascotuff 3000 Series (PEX 3004 Grey/PEH 3) using a power mixer for 3 minutes and then apply (preferably) by airless spray to a minimum DFT of 100–200 µm or WFT of 125-250 µm @ a theoretical spread rate of 5.3 m²/ℓ. Allow 16 hours to dry.

Finishing Coats

- ^ Apply two full coats of Plascon Waterbased Velvagro (VLW/TVW) to achieve complete obliteration, allowing 4 hours drying between coats.
NB: if white is used, three coats might be necessary to achieve obliteration.
-

TABLE REFERENCES:

- ^ Technical Data Sheet (TDS): User must always ensure that latest issue is used.
- ^ B = Brush (ready for use), R = Roller (synthetic, min. 10mm pile) (ready for use), S = Airless spray (ready for use).
- ^ Theoretical spreading rate quoted is for smooth non-porous substrates and does not include allowance for surface profile, porosity, wastage and uneven film application. Suitable allowance should be made according to type of work, method and skill of applicator. Practical spreading rate quoted is an average guide only - actual must be determined by user.
- ^ Overcoating times are at 23 °C and 75 % relative humidity. Longer times must be allowed under cooler and moist conditions. DO NOT paint during inclement weather and when temperature is below 10 °C.
- ^ Fading and chalking will occur to a greater or lesser degree depending on pigmentation and generic binder type.
- ^ NB: Life expectancy may vary, depending on environmental conditions and stresses, within the macro/micro climate of the project.

Copyright ©Kansai Plascon (Pty) Ltd 2013. All rights reserved. No part of this work may in any form or by any means be reproduced without prior written permission of the copyright owner. PLASCON is the registered trade mark of Kansai Plascon (Pty) Ltd,
