

WOODCARE WOOD PRESERVATIVE

PRODUCT CODE: FPR Range

TECHNICAL DATA SHEET

Dundret Description	A nonatrating all based asstics f	as the protection and waterproofing of outerior timber
Product Description	A penetrating oil based coating for the protection and waterproofing of exterior timber.	
Intended Uses	9 .	len window frames ,wooden doors, laminated sections, weather g, wood cladding and also prefabricated wooden building (domestic
Features & Benefits	 WOOD PRESERVATIVE corfor protection against fung 	ntains deep penetrating oils and waxes and an effective preservative al attack.
	• • •	even after prolonged exposure.
	 Protects preserves and bea 	utifies exterior woodwork
Product Information	Appearance Colours	Satin Clear (FPR 1), Light Oak (FPR 2), Teak (FPR 3), Oregon Pine (FPR 4) Imbuia (FPR 5) and Mahogany (FPR 6)
	Generic type	Oleoresinous with dry film preservatives
	Solids	Approx. 40 % by mass; 30 % by volume
	Viscosity at 23 °C	12 - 14 Sec FC4 (typical)
	S G	0,89 kg/ℓ (typical)
	Flash Point	38 °C
	Theoretical spreading rate	15 m²/ℓ @ 20μm DFT per coat. This serves as a guide only
	Practical spreading rate	The practical spreading rate will vary depending on the porosity an profile of the substrate, as well as the application technique and
		tools used.
	VOC	401 g/ €
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous an occasionally during use.
	Method	Brush or dipping.
	Thinning	Ready for use by brush. For dipping see application
	Cleaning	MINERAL TURPENTINE (AZH 1) or POLYCELL BRUSH CLEANER.
	Substrate	Well prepared wood surfaces.
	Application Environment	Surface Temperature Ambient Temperature Relative Humidity
		Min: 10 °C Min: 10 °C Min: 10%
		or 2 °C min. above dew point
		Max: 40 °C Max: 40 °C Max: 85 %
	Drying time	Touch dry 16 h at 23 °C
		Overcoating 24 h at 23 °C
Storage & Packaging	Store away from direct sun, heat	and severe cold.
	Packaging: 1L and 5L. Clear (FPR 1) only available in 2L	





WOODCARE WOOD PRESERVATIVE

PRODUCT CODE: FPR Range

Surface Preparation	All surfaces must be clean, dry and sound. Remove any oil, grease, mortar droppings, etc. 1. NEW WOOD: Sand in the direction of the grain, to a smooth finish with 150 grit paper. Remove dust with
	a damp cloth.
	2. PREVIOUSLY VARNISHED WOOD IN GOOD CONDITION:
	Sand to bare wood and remove varnish completely. Remove dust with a damp cloth.
	3. PREVIOUSLY VARNISHED WOOD IN POOR CONDITION:
	Strip completely by deep sanding or by using REMOVALL ALL PURPOSE PAINT REMOVER BRUSH/GEL GRADE (RRA220). Rinse thoroughly with fresh water. Allow to dry. Sand to a smooth finish. Remove dust with a damp cloth.
	4. WOOD PREVIOUSLY COATED WITH WAX SEALER/OIL BASED WOOD PRESERVATIVE:
	Mechanically sand until there is no evidence of residue. Wipe using a mutton cloth and solvent LACQUER THINNERS (ILS 1) to remove weathered material and restore surface to an even appearance. Multiple wipes might be necessary.
	 PREVIOUSLY PAINTED WOOD: Strip old paint by deep sanding or by using REMOVALL ALL PURPOSE PAINT REMOVER BRUSH/GEL GRADE (RRA220).
	Rinse thoroughly with fresh water. Allow to dry. Sand bare wood to a smooth finish .Remove dust with a damp cloth.
	6. DISCOLOURED OR WEATHERED WOOD:
	Remove discoloured or weathered layer by sanding with 100 grit paper. Sand to a smooth finish using 15
	grit paper. Remove dust with a damp cloth.
	7. KNOTS IN WOOD:
	Apply WOODCARE KNOT SEAL (PK 2). 8. FILLER (INTERIOR WOOD ONLY):
	If required use POLYCELL WOODFILLER. Sand smooth.
Application	Ready for use by brush application. Application by brush ensures the best penetration.
	If dipping is required, thin 4 parts WOOD PRESERVATIVE to 1 part MINERAL TURPENTINE (AZH 1) by
	volume.
	 Normally two coats are sufficient prior to installation. If the substrate is extremely porous thre applications may be necessary in order to produce an even finish. In that event the first coat soaks awa immediately, apply a further coat by dipping immediately to satisfy absorbency of the substrate. Allow t dry for 24 hours before applying finishing coat.
	N.B. To prevent moisture penetration, the back and end grain of all timber to be used for house gable
	hardwood door frames and window frames should be protected with two coats of WOOD PRESERVATIV (FPR Range).
Cautions	Do not use on toys and cots.
	Do not overcoat with paints and varnishes unless removed and washed down with lacquer thinners.
Safety	Always keep paint out of reach of children.
Precautions	Ensure good ventilation during application and drying.
	 If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner.
	 Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty o water and seek medical attention.
	 Harmful if swallowed. Seek medical attention and do not induce vomiting.
	Do not smoke while painting.
	Flammable. Store in a cool dry place away from heat and sparks.
	 Refer to Safety Data Sheet for complete information.





WOODCARE WOOD PRESERVATIVE

PRODUCT CODE: FPR Range

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

CAPE TOWN: DURBAN: **GAUTENG:** PORT ELIZABETH: P O Box 42 P.O. Box 4010 P O Box 1594 Private Bag X16 Luipaardsvlei 1743 Port Elizabeth 6000 Eppindust 7475 Mobeni 4060 Tel: (021) 505-2400 Tel: (031) 451-3200 Tel: (011) 951-4500 Tel: (041) 401-1400 Fax: (031) 451-3411 Fax: (011) 955-2841 Fax: (041) 453-4606 Fax: (021) 534-3791

PLASCON ADVISORY SERVICE: 0860 20 40 60

