

## PROFESSIONAL AQUARISTA

PRODUCT CODE: PHB 800 & THB Tint Base

### TECHNICAL DATA SHEET

<b>Product Description</b>	A durable pure acrylic emulsion paint with good flexibility and waterproofing properties.													
<b>Intended uses</b>	<ul style="list-style-type: none"> <li>Used as a waterproofing coating for plastered or bagged walls.</li> <li>For use on thoroughly cleaned and suitably primed cement, fibre cement and galvanised iron</li> </ul>													
<b>Features &amp; Benefits</b>	<ul style="list-style-type: none"> <li>Has low water absorption to prevent the ingress of moisture and as a result has improved waterproofing properties at the required film thickness</li> <li>Its good flexibility allows it to expand and contract over cracked surfaces.</li> <li>Good exterior durability with low dirt pick-up.</li> </ul>													
<b>Product Information</b>	Appearance Colour Tint Base Volume Solids Recommended DFT Recommended WFT Viscosity at 23 °C Theoretical spreading rate Practical spreading rate  VOC	Sheen White (PHB 800) Pastel Tint Base (THB 1000) 40 % 80 - 100 µm 200 -250 µm 120 - 125 KU 4.4 m²/L at 90 µm DFT. This serves as a guide only. The practical spreading rate will vary depending on the profile of the substrate, as well as the application technique and tools used. < 16 g/L for White < 5 g/L for Pastel base (tinted)												
<b>Application Details</b>	Mixing  Thinning Method Cleaning Drying time    Application Environment	Ready for use. Stir thoroughly with a flat paddle until homogeneous before use. Not Recommended Brush, roller or airless spray. Water Touch dry: 1 h @ 23 °C Over coating: 2 h @ 23 °C  <table border="1"> <thead> <tr> <th>Surface Temperature</th><th>Ambient Temperature</th><th>Relative Humidity</th></tr> </thead> <tbody> <tr> <td>Min: 10 °C</td><td>Min: 10 °C</td><td>Min: 10%</td></tr> <tr> <td colspan="3">or 3 °C min. above dew point</td></tr> <tr> <td>Max: 40 °C</td><td>Max: 40 °C</td><td>Max: 85%</td></tr> </tbody> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	or 3 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85%
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10%												
or 3 °C min. above dew point														
Max: 40 °C	Max: 40 °C	Max: 85%												
<b>Storage and Packaging</b>	Store away from direct sun, heat and severe cold. Packaging: 20 L.													
<b>Tint Bases</b>	<ul style="list-style-type: none"> <li>The tint base containers are underfilled to levels which are specific for each tint base to allow for a calculated volume of colourants to be added. The volume indicated on the container is only achieved after the addition of all prescribed colourants as per the formulation.</li> <li>The tint bases and the colourants are unfinished or intermediate products which are not recommended for use on their own. A finished product is only produced once the prescribed quantities of colourants have been thoroughly mixed with the tint base.</li> <li>When mixed to a finished product its technical features, product information, application and surface preparation details comply with that of <b>AQUARISTA (PHB 800)</b>  <b>Only colourants from the PLASCON INSPIRED COLOUR system are permitted for use when tinting.</b></li> </ul>													

## PROFESSIONAL AQUARISTA

PRODUCT CODE: PHB 800n & THB Tint Base

<b>Tinting Procedure</b>	<ul style="list-style-type: none"> <li>Select the required colour and reference no. from the <b>INSPIRED COLOUR</b> system, other suitable systems or colour cards and locate the applicable formulation from the tables.</li> <li>Certain colour choices may require more than two coats to achieve full obliteration (see computer formulations for details in remarks column prior to tinting)</li> <li>Select the required tint base and volume for tinting and set the tinting machine to deliver the correct amount of colourants as per formulation.</li> <li>Inject all required colourants, close container and shake on mechanical shaker for 5 minutes.</li> <li><b>Note: UNDER NO CIRCUMSTANCES SHOULD COLOURS BE TINTED FROM (PHB 800) White - USE ONLY THE PRESCRIBED TINT BASES</b></li> </ul>
<b>Surface Preparation</b>	<p>Ensure that surfaces are dry, free from dirt, grease and oil and loose and flaking paint. Repair surface defects with the appropriate <b>POLYCELL POLYFILLA</b> product.</p> <ol style="list-style-type: none"> <li><b>NEW OR WEATHERED GALVANISED IRON:</b> Clean thoroughly with <b>GALVANISED IRON CLEANER (GIC 1)</b> and prime with <b>PLASCON GALVANISED IRON PRIMER (GIP 1)</b>.</li> <li><b>POROUS CEMENT PLASTER AND OTHER MASONRY SURFACES:</b> Apply one coat of <b>PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700)</b>.</li> <li><b>FIBRE-CEMENT SHEETING:</b> Apply <b>BONDING LIQUID (CVI 14)</b>.</li> <li><b>STEEL:</b> Remove any rust and prime with <b>ZINC PHOSPHATE PRIMER (UC 170)</b>.</li> </ol>
<b>Application</b>	<ul style="list-style-type: none"> <li><b>WHEN USED AS A WALL COATING:</b> Apply two coats <b>PROFESSIONAL AQUARISTA</b> at an average spreading rate of 4 m<sup>2</sup>/L.</li> <li>Allow at least two hours drying between coats.</li> </ul>
<b>Caution</b>	<ul style="list-style-type: none"> <li><b>NOT</b> suitable to seal concrete dams or ponds or surfaces permanently immersed in water.</li> <li>Not to be used on roofs as a topcoat.</li> <li><b>Tinting can negatively influence product properties.</b></li> <li>Avoid painting during inclement weather or if temperature is below 10 °C</li> </ul>
<b>Safety Precautions</b>	<ul style="list-style-type: none"> <li>Keep out of reach of children.</li> <li>Ensure good ventilation during application and drying.</li> <li>In case of skin contact, wash with soap and water or a recognised skin cleaner.</li> <li>Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.</li> <li>Harmful if swallowed. Do not induce vomiting. Seek medical attention.</li> <li>Refer to Safety Data Sheet for complete information.</li> </ul>

### **DISCLAIMER:**

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

**NB:** Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

**NB: TO ORDER:** Quote product name, product code number, packaging and colour.

### **KANSAI PLASCON (PTY) LIMITED**

10 Frederick Cooper Drive,  
Factoria, Krugersdorp  
South Africa  
1739.  
Tel: +27 11 951 4500  
Fax: +27 800 110 932

**PLASCON ADVISORY SERVICE:** 0860 20 40 60

**EMAIL:** advice@kansaiplascon.co.za