

Technical Data Sheet

Date of Issue: 30/09/2022 Revision Date 30/09/2022 | Version 2.0

Product name

FLOORTECT 4000 SF CURING AGENT



PLASCOGUARD 4000 HB CURING AGENT(KAT 521)

PRODUCT DESCRIPTION

Cycloaliphatic amine curing agent for 2 pack epoxy systems.

INTENDED USES

Used to cure the FLOORTECT 4000 SF(FHB 4000 RANGE)

PRODUCT INFORMATION

Appearance Colourless liquid

Flash Point 96°C

Viscosity 60 - 70seconds (typical) Ford Cup No.4

APPLICATION DETAILS

Mixing Ratio 1 part curing agent(KAT 521) to 3 parts base(FHB 4000) by

volume

Mixing Stir both components separately with a power mixer until homogenous.

Add the curing agent to the base and mix thoroughly together. Mix only

in proportions shown above. Do not split packs.

Drying Time Touch dry 5h at 23°C

Overcoating (Min) 8h at 23°C
Overcoating (Max) 18h at 23°C
Dry to handle 24h at 23°C
Full Cure 7 Days





FLOORTECT 4000 SF CURING AGENT (KAT 521)

Technical Data Sheet

Date of Issue:30/09/2022 Revision Date 30/09/2022 \mid Version 2.0

Pot Life(Working) 20 min at 23°C

STORAGE AND PACKAGING

Store away from direct sun, heat, open flames, sparks and severe cold.

Shelf Life: 24 months(base)

24 months(curing agent)

Dual Packs: 20L unit: 15L in 20L container(base)

5L in 5L container (curing agent)

SAFETY PRECAUTIONS

- Always keep paint out of reach of children.
- Ensure good ventilation during application and drying.
- If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner.
- Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention.
- Harmful if swallowed. Seek medical attention and do not induce vomiting.
- Do not smoke while painting.
- Flammable. Store in a cool dry place away from heat and sparks.
- Refer to Safety Data Sheet for complete information.

DISCLAIMER

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging, and colour.

KANSAI PLASCON (PTY) LTD

10 Frederick Cooper Drive, Factoria, Krugersdorp South Africa 1739.





FLOORTECT 4000 SF CURING AGENT (KAT 521)

Technical Data Sheet

Date of Issue:30/09/2022 Revision Date 30/09/2022 | Version 2.0

Tel: +27 11 951 4500 Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za

