

**NEW WORK/REPAINT:** REPAINT – EXTERIOR/INTERIOR – DEMARCATION LINES (Obliterating Lines)

**SUBSTRATE:** Bituminous Screeds (excluding slurry surfaces)

**PAINT FINISH:** Road Marking Paint Black – Municipal  
Single pack solvent-based coating for obliterating demarcation lines

**PRODUCT CODE: TP 28**

**COLOUR:** Black

**ENVIRONMENT:** **The Maintenance Cycle is a guide but can vary due to micro-climate changes identified on the site which will affect the longevity of the coating system**

As per ISO 12944: Maintenance Cycle (Years) depending on traffic

|      |                  |   |
|------|------------------|---|
| C1 - | Inland           | 2 |
| C3 - | Industrial       | 2 |
| C5 - | Coastal / Marine | 2 |

| Plascon Coating System  | Application Method | Spreading Rate<br>m <sup>2</sup> /ℓ | WFT/DFT<br>μm<br>(min & max) | Reducer/<br>Cleaner    | Overcoating<br>time<br>h @ 23 °C | Technical<br>Data Sheet<br>No | TVOC<br>g/ℓ |
|---|--------------------|-------------------------------------|------------------------------|------------------------|----------------------------------|-------------------------------|-------------|
| <b>Finishing Coat</b><br>Plascon Road Marking Paint Black – Municipal (TP 28) | B, R or S          | @ 200 μm<br>Theo: 2.8<br>Prac: 2.0  | WFT 346-382<br>DFT 190-210   | Toluol Reducer (HVL 1) | 1.5                              | TP 28                         | 618         |

**NB:** \* practical spreading rate is dependent on surface porosity and profile

**SURFACE PREPARATION:**

- ^ Ensure bituminous screeds have cured for a minimum of three months.
- ^ Clean with Polycell Sugar Soap to remove oil, grease and other contaminants.
- ^ Rinse thoroughly with fresh water and allow to dry.

**APPLICATION:**

**Finishing Coat**

- ^ Apply one coat of Plascon Road Marking Paint Black - Municipal (TP 28) to a DFT of 190-210 μm.

**TABLE REFERENCES:**

- ^ Technical Data Sheet (TDS): User must always ensure that latest issue is used.
- ^ B = Brush (ready for use), R = Roller (synthetic, min. 10mm pile) (ready for use), S = Airless spray (ready for use).
- ^ Theoretical spreading rate quoted is for smooth non-porous substrates and does not include allowance for surface profile, porosity, wastage and uneven film application. Suitable allowance should be made according to type of work, method and skill of applicator. Practical spreading rate quoted is an average guide only - actual must be determined by user.
- ^ Overcoating times are at 23 °C and 75 % relative humidity. Longer times must be allowed under cooler and moist conditions. DO NOT paint during inclement weather and when temperature is below 10 °C.
- ^ Fading and chalking will occur to a greater or lesser degree depending on pigmentation and generic binder type.
- ^ NB: Life expectancy may vary, depending on environmental conditions and stresses, within the macro/micro climate of the project.

Copyright ©Kansai Plascon (Pty) Ltd 2013. All rights reserved. No part of this work may in any form or by any means be reproduced without prior written permission of the copyright owner. PLASCON is the registered trade mark of Kansai Plascon (Pty) Ltd,

---