

SPECIFICATION NO: **NW292**

NEW WORK/REPAINT: NEW WORK – INTERIOR/EXTERIOR

SUBSTRATE: Cast Iron / Wrought Iron

PAINT FINISH: Plascon Super Universal Enamel (Smooth superior high gloss enamel) **PRODUCT CODE: NY 1 / G**

COLOUR: White and standard colours as per colour card, plus Plascon colour system and other fan decks.

ENVIRONMENT: **The Maintenance Cycle is a guide but can vary due to micro-climate changes identified on the site which will affect the longevity of the coating system**

As per ISO 12944-2:1998 Maintenance Cycle (Years)

C1 -	Inland	2
C3 -	Industrial	2
C5 -	Coastal / Marine	2

Plascon Coating System	Application Method	Spreading Rate m ² /ℓ	WFT/DFT μm (min & max)	Reducer/Cleaner	Overcoating time h @ 23 °C	Technical Data Sheet No	TVOC g/ℓ
Primer Plascon Plascoprime PA-10 (BPA 410)	B, R or S	@ 17.5 μm Theo: 7.4 Prac: 3.6	WFT 76-192 DFT 10-25	PA-10 Thinner (CTH 5)	1	BPA 410	645
1st Finishing Coat Plascon Super Universal Enamel (NY 1/G/TSE)	B, R or S	@ 30 μm Theo: 16.3 Prac: 9	WFT 51-71 DFT 25-35	Min. Turps (AZH 1)	16	NY 1/G	381 white < 415 tint bases
2nd Finishing Coat Plascon Super Universal Enamel (NY 1/G/TSE)	B, R or S	@ 30 μm Theo: 16.3 Prac: 9	WFT 51-71 DFT 25-35	Min. Turps (AZH 1)	16	NY 1/G	381 white < 415 tint bases

SURFACE PREPARATION:

- ^ Surfaces must be clean, dry and rust free. Remove surface contaminants using Plascon Metalcare Aquasolv Degreaser (GR 1), scrubbing with bristle brush or broom, or using Scotch Brite pads. Rinse thoroughly with tap water while brushing or use hydroblast to remove all traces of Plascon Metalcare Aquasolv Degreaser (GR 1) to achieve a water break-free surface. Dry surface rapidly to prevent flash rust formation. Cleaned surface must be painted within 4 hours.
 - ^ After degreasing sand off rust to bright metal with coarse emery paper or scrape and wire brush to ISO 8501 - 01 : 2007 – St 3. Remove dust.
-

APPLICATION:

Primer Coat

- ^ Apply one coat of Plascon Plascoprime PA -10 (BPA 410) to entire substrate. For spray application thin with a minimum amount of PA-10 Thinner, not to exceed 20 % by volume. Allow 1 hour to dry.

Finishing Coats

- ^ Apply two full coats of Plascon Super Universal Enamel (NY 1/G/TSE) to achieve complete obliteration, allowing 16 hours drying between coats.
NB: if white is used, three coats might be necessary to achieve obliteration.
-

TABLE REFERENCES:

- ^ Technical Data Sheet (TDS): User must always ensure that latest issue is used.
- ^ B = Brush (ready for use), R = Roller (synthetic, min. 10mm pile) (ready for use), S = Airless spray (ready for use).
- ^ Theoretical spreading rate quoted is for smooth non-porous substrates and does not include allowance for surface profile, porosity, wastage and uneven film application. Suitable allowance should be made according to type of work, method and skill of applicator. Practical spreading rate quoted is an average guide only - actual must be determined by user.
- ^ Overcoating times are at 23 °C and 75 % relative humidity. Longer times must be allowed under cooler and moist conditions. DO NOT paint during inclement weather and when temperature is below 10 °C.
- ^ Fading and chalking will occur to a greater or lesser degree depending on pigmentation and generic binder type.
- ^ NB: Life expectancy may vary, depending on environmental conditions and stresses, within the macro/micro climate of the project.

Copyright ©Kansai Plascon (Pty) Ltd 2013. All rights reserved. No part of this work may in any form or by any means be reproduced without prior written permission of the copyright owner. PLASCON is the registered trade mark of Kansai Plascon (Pty) Ltd,
