

NEW WORK/REPAINT: NEW WORK - EXTERIOR – ROOFS/CLADDING

SUBSTRATE: Aluminum

PAINT FINISH: Plascon Nuroof Cool Acrylic Roof Paint
(Premium quality acrylic roof paint) **PRODUCT CODE: TRP 200**

COLOUR: Standard colours as per colour card

ENVIRONMENT: **The Maintenance Cycle is a guide but can vary due to micro-climate changes identified on the site which will affect the longevity of the coating system**

As per ISO 12944: Maintenance Cycle (Years)

C1 -	Inland	12
C3 -	Industrial	12
C5-	Coastal/Industrial	12

Plascon Coating System	Application Method	Spreading Rate m ² /ℓ	WFT/DFT μm (min & max)	Reducer/ Cleaner	Overcoating time h @ 23 °C	Technical Data Sheet No	TVOC g/ℓ
Primer Plascon Epiwash Strontium Chromate Primer (AW 255/KAT 508) Mixing ratio 1:1 by volume	B or S	@ 25 μm Theo: 9.6 Prac: 5.1	WFT 83-125 DFT 20-30	GP Epoxy Reducer (EPT 1) Or Epiwash Thinner (TH 128)	4 2 weeks max	AW 255	618
1st Finishing Coat Plascon Nuroof Cool Acrylic Roof Paint (TRP 200)	B, R or S	@ 42.5 μm Theo: 8.5 Prac: 5	WFT 100-140 DFT 35-50	Water	2	TRP 200	40
2nd Finishing Coat Plascon Nuroof Cool Acrylic Roof Paint (TRP 200)	B, R or S	@ 42.5 μm Theo: 8.5 Prac: 5	WFT 100-140 DFT 35-50	Water	2	TRP 200	40

SURFACE PREPARATION:

CONTAMINATION REMOVAL- Plascon Metalcare Aquasolv Degreaser (GR1)

- ^ Abrade and clean entire surface using Scotch Brite pads in conjunction with Plascon Metalcare Aquasolv Degreaser (GR 1) to emulsify surface contaminants. Rinse thoroughly with tap water to remove all traces of Plascon Metalcare Aquasolv Degreaser (GR 1). Test Area for water-break free surface. If not, repeat the process.
 - ^ Polished Aluminium – sand first with 100 grit paper to roughen the profile in order to provide a key for painting, before using Plascon Metalcare Aquasolv Degreaser (GR 1).
 - ^ Ensure that surfaces are clean, dry and sound
-

APPLICATION:

Primer Coat

Mix base and hardener thoroughly in a 1:1 ratio by volume before use.

- ^ Apply one coat of Plascon Epiwash Strontium Chromate Primer (AW 255) to achieve a continuous film. Allow minimum 4 hours to dry.

Finishing Coats

- ^ Apply two full coats of Plascon Nuroof Cool Acrylic Roof Paint (TRP 200) to achieve complete obliteration, allowing 2 hours drying between coats.
-

TABLE REFERENCES:

- ^ Technical Data Sheet (TDS): User must always ensure that latest issue is used.
- ^ B = Brush (ready for use), R = Roller (synthetic, min. 10mm pile) (ready for use), S = Airless spray (ready for use).
- ^ Theoretical spreading rate quoted is for smooth non-porous substrates and does not include allowance for surface profile, porosity, wastage and uneven film application. Suitable allowance should be made according to type of work, method and skill of applicator. Practical spreading rate quoted is an average guide only - actual must be determined by user.
- ^ Overcoating times are at 23 °C and 75 % relative humidity. Longer times must be allowed under cooler and moist conditions. DO NOT paint during inclement weather and when temperature is below 10 °C.
- ^ Fading and chalking will occur to a greater or lesser degree depending on pigmentation and generic binder type.
- ^ NB: Life expectancy may vary, depending on environmental conditions and stresses, within the macro/micro climate of the project.

Copyright ©Kansai Plascon (Pty) Ltd 2013. All rights reserved. No part of this work may in any form or by any means be reproduced without prior written permission of the copyright owner. PLASCON is the registered trade mark of Kansai Plascon (Pty) Ltd,
