

**NEW WORK/REPAINT:** NEW WORK - EXTERIOR – ROOFS  
**UP TO 1 KM FROM THE COAST AND INCLUDES INDUSTRIAL FALLOUT AREAS**  
**(Only for galvanizing in good condition)**

**SUBSTRATE:** Galvanized Steel

**PAINT FINISH:** Plascon Nuroof Cool Acrylic Roof Paint PRODUCT CODE: **TRP 200**  
(Premium quality acrylic roof paint with infrared reflective technology)

**COLOUR:** Standard colours as per colour card

**ENVIRONMENT:** **The Maintenance Cycle is a guide but can vary due to micro-climate changes identified on the site which will affect the longevity of the coating system**

As per ISO 12944: Maintenance Cycle (Years)

C1 -	Inland	12
C3 -	Industrial	12
C5 -	Coastal / Marine	12

Plascon Coating System	Application Method	Spreading Rate m <sup>2</sup> /ℓ	WFT/DFT μm (min & max)	Reducer/ Cleaner	Overcoating time h @ 23 °C	Technical Data Sheet No	TVOC g/ℓ
<b>Primer</b> Plascon Aquanova Primer (WHP 1)	B, R or S	@ 55 μm Theo: 6.7 Prac: 4.4	WFT 135-162 DFT 50-60	Water	2	WHP 1	11
<b>1<sup>st</sup> Finishing Coat</b> Plascon Nuroof Cool Acrylic Roof Paint (TRP 200)	B, R or S	@ 42.5 μm Theo: 8.5 Prac: 5	WFT 100-140 DFT 35-50	Water	2	TRP 200	40
<b>2<sup>nd</sup> Finishing Coat</b> Plascon Nuroof Cool Acrylic Roof Paint (TRP 200)	B, R or S	@ 42.5 μm Theo: 8.5 Prac: 5	WFT 100-140 DFT 35-50	Water	2	TRP 200	40

**SURFACE PREPARATION:**

**ENSURE THAT THE ROOF HAS BEEN WATERPROOFED**

**GALVANISED IRON IN GOOD CONDITION**

- ^ Apply Plascon Galvanised Iron Cleaner (GIC 1) to all bare Galvanised areas by brush, broom or spray. Allow to react for 1 minute. Rinse off with tap water using bristle brooms, brushes or Scotch Brite pads to remove all surface contaminants. Test area for water-break free surface. If not, repeat the cleaning process. Allow to dry completely.
- 

**APPLICATION:**

**Primer Coat**

- ^ Apply one coat of Plascon Aquanova Primer (WHP 1) to achieve a continuous film. Allow 2 hours to dry.

**Finishing Coats**

- ^ Apply two full coats of Plascon Nuroof Cool Acrylic Roof Paint (TRP 200) to achieve complete obliteration, allowing 2 hours drying between coats.
- 

**TABLE REFERENCES:**

- ^ Technical Data Sheet (TDS): User must always ensure that latest issue is used.
- ^ B = Brush (ready for use), R = Roller (synthetic, min. 10mm pile) (ready for use), S = Airless spray (ready for use).
- ^ Theoretical spreading rate quoted is for smooth non-porous substrates and does not include allowance for surface profile, porosity, wastage and uneven film application. Suitable allowance should be made according to type of work, method and skill of applicator. Practical spreading rate quoted is an average guide only - actual must be determined by user.
- ^ Overcoating times are at 23 °C and 75 % relative humidity. Longer times must be allowed under cooler and moist conditions. DO NOT paint during inclement weather and when temperature is below 10 °C.
- ^ Fading and chalking will occur to a greater or lesser degree depending on pigmentation and generic binder type.
- ^ NB: Life expectancy may vary, depending on environmental conditions and stresses, within the macro/micro climate of the project.

Copyright ©Kansai Plascon (Pty) Ltd 2013. All rights reserved. No part of this work may in any form or by any means be reproduced without prior written permission of the copyright owner. PLASCON is the registered trade mark of Kansai Plascon (Pty) Ltd,

---