

NEW WORK/REPAINT: NEW WORK - EXTERIOR - ROOFS

SUBSTRATE: Galvanised Iron Roofs

PAINT FINISH: Plascon Professional Roof Paint (UV resistant roof coating) **PRODUCT CODE: PRP**

COLOUR: Standard Colours Only

ENVIRONMENT: **The Maintenance Cycle is a guide but can vary due to micro-climate changes identified on the site which will affect the longevity of the coating system**

As per ISO 12944: Maintenance Cycle (Years)

C1 -	Inland	4
C3 -	Industrial	3
C5 -	Coastal / Marine	3

Plascon Coating System	Application Method	Spreading Rate m ² /ℓ	WFT/DFT μm (min & max)	Reducer/Cleaner	Overcoating time h @ 23 °C	Technical Data Sheet No	TVOC g/ℓ
Primer Plascon Galvanized Iron Primer (GIP 1)	B, R or S	@ 30 μm Theo: 13 Prac: 7	WFT 64-102 DFT 25-40	Water	WB topcoat: 4-6 SB topcoat: 24	GIP 1	20
1st Finishing Coat Professional Roof Paint (PRP)	B, R or S	@ 42.5 μm Theo: 5.9 Prac: 3.5	WFT 140-200 DFT 35-50	Water	2	PRP	< 20
2nd Finishing Coat Professional Roof Paint (PRP)	B, R or S	@ 42.5 μm Theo: 5.9 Prac: 3.5	WFT 140-200 DFT 35-50	Water	2	PRP	< 20

SURFACE PREPARATION:

GALVANISED IRON IN GOOD CONDITION

- ^ Apply Plascon Galvanised Iron Cleaner (GIC 1) to all bare Galvanised areas by brush, broom or spray. Allow to react for 1 minute. Rinse off with tap water using bristle brooms, brushes or Scotch Brite pads to remove all surface contaminants. Test area for water-break free surface. If not, repeat the cleaning process. Allow to dry completely.

OLD GALVANISED IRON PARTIALLY RUSTED

- ^ Where the Zinc has been depleted the corroded areas must be prepared to ISO 8501-1: 2007 St 3 (bright metal finish, e.g. mechanical wire brushing). Patch Prime using Plascon Plascotuff 3000 (PEX 3004 Grey/PEH 3 Mixing ratio 4:1 by volume) to a DFT of 100–200 µm or WFT of 125–250 µm @ a theoretical spread rate of 5.3 m²/ℓ. Allow 16 hours to dry.
-

APPLICATION:

Primer Coat:

- ^ Apply one coat of Plascon Galvanised Iron Primer (GIP 1) to achieve a continuous film. Allow 4-6 hours drying time (water based topcoat) or 24 hours drying time (solvent based topcoat).

Finishing Coats

- ^ Apply two coats of Plascon Professional Roof Paint (PRP) allowing 2 hours drying time between coats.
-

TABLE REFERENCES:

- ^ Technical Data Sheet (TDS): User must always ensure that latest issue is used.
- ^ B = Brush (ready for use), R = Roller (synthetic, min. 10mm pile) (ready for use), S = Airless spray (ready for use).
- ^ Theoretical spreading rate quoted is for smooth non-porous substrates and does not include allowance for surface profile, porosity, wastage and uneven film application. Suitable allowance should be made according to type of work, method and skill of applicator. Practical spreading rate quoted is an average guide only - actual must be determined by user.
- ^ Overcoating times are at 23 °C and 75 % relative humidity. Longer times must be allowed under cooler and moist conditions. DO NOT paint during inclement weather and when temperature is below 10 °C.
- ^ Fading and chalking will occur to a greater or lesser degree depending on pigmentation and generic binder type.
- ^ NB: Life expectancy may vary, depending on environmental conditions and stresses, within the macro/micro climate of the project.

Copyright ©Kansai Plascon (Pty) Ltd 2013. All rights reserved. No part of this work may in any form or by any means be reproduced without prior written permission of the copyright owner. PLASCON is the registered trade mark of Kansai Plascon (Pty) Ltd,
